Technical Specification Sheet

Kingdom Plywood

KINGDOM
M D F

MR MDF

Core Color	Green
Density	700-900 kg/cu.mtr.
Formaldehyde Emission Standard	E1, E2
Thickness	2mm, 2.5mm, 2.7mm, 3mm, 3.2mm, 3.6mm, 4mm, 4.8mm, 5mm, 6mm, 7mm, 8mm, 9mm, 10mm, 11mm, 12mm, 15mm, 16mm, 17mm, 18mm, 20mm, 22mm, 25mm
Size	1220x2440mm, 1830x2440mm
Thickness Tolerance	< +/- 0.2 mm
Thickness Swell (24 hrs)	8%
Thickness Swell after cyclic testing	8%
Internal Bond	68kg
Internal Bond after cyclic testing	14kg
Moisture Content	5-7%
Surface	Sanded, Matt, Grooved
Production Process	Semi-Dry
Facing Type	Single-Faced, Double-Faced
Application	Indoor usages such as Furniture, Construction, Decoration, Door, Flooring, Wall Panel, Packaging etc.

• The results indicated in the table above refer to average values obtained in laboratory tests. However, there could be small variations in the tests reproduced in other laboratories and under other usage conditions.

• "Kingdom Quality Promise" - We will continuously try to improve the specifications mentioned here as part of our DNA of Continuous Improvement and of delivering Value to our customers each and every time.

Email: info.hk@kingdomrg.com
Web: www.kingdomrg.com | www.kingdompanels.com